



# Highly flexible gel adhesive C2TE GEOFLEX white

## 25kg



Brand	ATLAS
Manufacturer	
Country of manufacture	Poland
Weight	25.00 kg
Product Code	GEOFLEX-BIALY-25
EAN	5905400314816
SKU	8078
Advice IBB	
Application	For the most demanding substrates, including underfloor heating, plasterboards, OSB
IBB ID	8078

### Product specification

Manufacturer	ATLAS	Unit	plastic bag
Brand	atlas	Colour	white
EAN	5905400314816	Country of manufacture	Poland
Relative air humidity during application and curing	< 80%	Density of the finished product	ca 1.9 g/cm3
		pH	8

**ATLAS GEOFLEX WHITE** highly flexible gel adhesive 2-15 mm

#### Most important features

- ideal for ceramic, porcelain, glass mosaic, natural stone
- for tile on tile, OSB, terrace, balcony, underfloor heating
- bed depth up to 15 mm
- non-slip - even with large tiles
- excellent spread beneath a tile

#### Product description

ATLAS GEOFLEX WHITE is a white C2TE adhesive for tiles for internal and external application on wall and floor. Ideal for natural stone, porcelain and glass mosaic. Wide range of bed thickness from 2 up to 15 mm.

No slip from the wall – cladding can be installed from the top of the wall with no additional support.

Walking on and grouting just after 12 hours – owing to accelerated proces of adhesive setting and drying.nder, aggregates and selected modifying agents.

For application in temperature from 5°C up to 35°C.

### **Gel technology**

The unique gel technology used in ATLAS GEOFLEX WHITE brings the following advantages:

- adhesive is suitable for any type of cladding: natural stone, glass mosaic, ceramic, porcelain,
- consistency of adhesive can be adjusted to individual preferences of the tiler and needs of specific job – mixing ratio is much wider than in case of traditional adhesives,
- bed depth up to 15 mm – substrate levelling and tiling at once,
- full spread under the tile with higher mixing ratio – ensured adhesion and durable bond, which is relevant for exterior use,
- safe cladding installation on surfaces exposed to direct sunlight – during fixing cladding, as well as during mortar setting (e.g. on balcony, terrace).

### **Technical data**

Mixing ratio (water/dry mix) 0,26 ÷ 0,33 l / 1 kg

Min./max. bed depth 2 mm / 15 mm

Pot life approx. 4 hours

Open time min. 30 minutes

Floor access/ grouting after 12 hours