



Acrylic render TESORO dotted 1.5 mm white 25 kg



Manufacturer	
Country of manufacture	Poland
Weight	25.00 kg
Product Code	TESORO
EAN	5908249170049
SKU	001183
IBB ID	11042

Product specification

Manufacturer	SEMPRE	Unit	bucket
Colour	white	EAN	5908249170049
Country of manufacture	Poland		

Acrylic render TESORO dotted 1.5 mm

intended for making decorative and protective coatings in the SEMPER TERM ST building insulation system and for use outside buildings on typical construction substrates, also coated with acrylic paints. The product is applied with a trowel. Available in a range of colors corresponding to the IMPRESSIO and MASSIMO color palettes or dyed based on the supplied pattern. Before applying the plaster, prime the substrate with TESORO GRUNT or MULTIGRUNT.

Product features:

- easy to apply and invoice with a trowel
- a wide range of colors
- a large selection of structures and granulations
- increased resistance to algae and fungi
- high flexibility after drying
- high color stability
- high mechanical resistance
- excellent adhesion to the substrate
- granulation: 1-3mm / structure: lamb / bark beetle
- pallet 600kg / 25kg x 24pcs

The substrate should be clean, load-bearing, compact, even and degreased. Loose grains and impurities as well as poorly bonded coatings of old emulsion paints must be thoroughly removed.

Any irregularities and cavities should be supplemented with appropriate leveling mortars (BUDOMONT ZT-620, BUDOMONT ZS640).

Surfaces infected with fungi and algae must be disinfected with ALGHESIL algae and fungus remover.

In the case of new cement plasters, a minimum two-week seasoning period should be maintained.

Priming

24 hours before applying the plaster mass, the substrate should be primed with the TESORO GRUNT or MULTI GRUNT primer.

Application

Apply the plaster to the thickness of the grain with a stainless steel trowel. The appropriate thickness of the plaster is obtained by several times using a steel trowel.

Immediately trowel the surface prepared in this way with a plastic trowel until the desired texture is obtained.

Plaster with a full structure is rubbed with circular movements of the trowel, while plaster with a scratched structure - with longitudinal movements. It is recommended to work at a temperature of 5 to 25°C. Do not use on sunny surfaces and in rainy weather.

Thinning

The product is ready to use. If necessary, dilute with water in an amount not exceeding 1%. Too much dilution may cause a reduction in hiding power, which results in the appearance of discoloration.

Drying up

At a temperature of 20°C and relative air humidity of 55%, the drying time of the coating is approx. 24 hours.

Complete hardening occurs after approx. 48 hours.

Low temperature and increased air humidity extend the drying time, even by several days.

Until it is completely dry, protect the expedition against precipitation. Clean with water immediately after use.